



Technical Information

| | | |
|---------------------|---|---|
| Product name | : | MoTip Kompakt Clear Varnish, high gloss |
| Article number | : | 50000 |
| Supplier / Producer | : | MOTIP DUPLI B.V. Wolfraamweg 2 NL-8471 XC WOLVEGA |
| Telephone number | : | +31 561 – 69 44 00 |
| Telefax number | : | +31 561 – 69 44 31 |

Product description

High quality finish to create a high-gloss preservative for all car repair lacquers.

Product characteristics

Fast drying
Excellent filling property
Excellent flow
Lasting gloss
Scratch free and shock proof
Resistant to weather influences
UV resistant and non-fading
Excellent adhesion

Physical and Chemical Characteristics

| | | |
|-----------------------|---|----------------------------------|
| Contents | : | 400 ml |
| Base | : | Acrylic resin |
| VOC-content | : | Approximately 90% w/w |
| Solid content | : | Approximately 10% w/w |
| Gloss | : | High gloss 90 at an angle of 60° |
| Coverage | : | 1,25 to 1,75 m ² |
| Dust dry | : | After 5 to 10 minutes |
| Tack free | : | After 10 to 20 minutes |
| Hardened/re-sprayable | : | After 2 hours |
| Heat resistant | : | To 110°C |

Usage

Before use, carefully read the directions on the packaging and act accordingly.

Pre Treatment

The surface should be clean, dry and free of grease. Slightly sand the surface (grain 600).

Treatment

The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 15 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimetre.

Apply the clear varnish in several thin layers. Before applying the next layer, again shake the aerosol.

After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

The drying time depends on the ambient temperature, the humidity of the air and the thickness of the lacquer applied.